

STYLE: THERMOZITE

DATE: 9/17/07

TEST METHOD	PROPERTY	SPECIFICATION
N/A	CONSTRUCTION	100% ecofi® Polyester Nonwoven Material with Thermobonded Metalized Film (One Side)
FTM NW508 (ASTM D3776)	WEIGHT	29.5 oz/yd ² +/-3.0 oz/yd ²
FTM NW502 (ASTM D3774)	WIDTH	As Requested +0.5 in / -0 in
FTM NW504 (ASTM D5729)	THICKNESS	0.350 in +/-0.050 in
FMVSS302	FLAMMABILITY	MD 4.0 in/min max CMD 4.0 in/min max
ASTM C177-97	THERMAL CONDUCTIVITY	0.280 K
ASTM C177-97	THERMAL RESISTANCE	1.3 R
ASTM C423-99A ASTM E795-93	NOISE REDUCTION COEFFICIENT	0.30 Hz
VISUAL	COLOR	Match Approved Standard
VISUAL	APPEARANCE	Match Approved Standard

REVISIONS

DATE	DESCRIPTION	BY
11/22/96	FIRST ISSUE	T.N.
9/17/07	Rev 1: add thermal cond. & res. / noise reduction	T.N.